

# **Biaxial Geogrids** Technical Datasheet

Lotrak<sup>®</sup> Premium Biaxial Geogrids are designed and manufactured to provide ground stabilisation and reinforcement. High strength, combined with low elongation provides effective reinforcement. The aperture design of the geogrid allows the aggregate to interlock and encourages load dispersal, particularly in applications such as paved/ unpaved roads and woring platforms to name a few.

Using a geogrid as part of a civil engineering or construction project results in a significant reduction to the quantity of required fill material, as Lotrak<sup>®</sup> geogrids can increase the bearing capacity of the underlying ground offering enhanced performance and cost benefits to the overall project.

### **Product Features**

- The high strength and with low elongation of Lotrak<sup>®</sup> provides effective ground reinforcement
- The aperture design of Lotrak<sup>®</sup> geogrids enables aggregate materials to interlock and encourages load dispersal
- Lotrak<sup>®</sup> geogrids are manufactured under ISO Quality Management and the Construction Products Regulation

## Benefits

- Lotrak<sup>®</sup> Geogrids are durable for more than 100 years
- Provides Effective Soil & Aggregate Confinement
- Excellent Mechanical Properties
- High-performance Reinforcement
- Cost Effective Design Component
- Aperture sizes to suit various granular particles

Don & Low Ltd, Glamis Road, Forfar, Angus, DD8 1FR, Scotland, UK t: +44(0) 1307 452200, e: lotrak@donlow.co.uk w: **www.donlow.co.uk** 









TEST	STANDARD		LOTRAK®			
Product			20/205	30/30S	40/40S	30/30L
Tensile Strength (kN/m)	EN ISO 10319	MD	20	30	40	30
		CD	20	30	40	30
Tensile Strength at 2% strain (%)	EN ISO 10319	MD	7	10.5	15	9
		CD	7	10.5	15	9
Tensile Strength at 5% strain (%)	EN ISO 10319	MD	14	20	30	20
		CD	14	20	30	20
Elongation at max. load (%)	EN ISO 10319	MD	15	12	9	12
		CD	11	12	10	9
PHYSICAL ATTRIBU	JTES					
Grid Spacing/ Aperture (mm)	caliper		36 x 36	36 x 36	36 x 36	60x60
Rib Thickness (mm)	caliper	MD/CD	1.3/0.9	2.0/1.6	2.5/1.7	2.9/2.0
Rib Width (mm)	caliper	MD/CD	2.6/2.8	2.7/3.0	3.5/4.4	5.5/6.0
Junction Height (mm)	caliper		3.3	4.8	5.0	6.4
Carbon Black (%)	ASTN D 1603		≥2	≥2	≥2	≥2
Effect of UV Light			The polypropylene (PP) used contains a UV inhibitor			
Roll Size (m)			3.95 x 50	3.95 x 50	3.95 x 50	3.95 x 50

#### All products are manufactured under BS EN ISO 9001.

#### Notes & Declaration

Please note that the product is to be covered within 1 month of installation. Lotrak range of geogrids are predicted to be <u>durable for more than 100 years</u> in soil temperatures  $\leq 25^{\circ}$ . The Lotrak<sup>®</sup> range of geogrids are resistant to highly acid and alkaline environments on the basis of a durability assessment. In regard to dangerous substances, Don & Low Lotrak<sup>®</sup> geogrids contain less than required by national regulations in EU member states.

Don & Low reserves the right to change specifications or other product information. Don & Low accepts no responsibility or liability for information provided by third parties. No warranties, express or implied, are offered regarding the suitability of any product for your use, as site conditions and customer requirements vary. Should you require further information, please contact us. Products are sold subject to the seller's terms and conditions of sale. No warranty or immunity is offered against infringement of patents or other intellectual property rights.

©Don & Low Limited, 2024. The intellectual property in the products is owned and protected by Don & Low or its licensors.

Don & Low Ltd, Glamis Road, Forfar, Angus, DD8 1FR, Scotland, UK t: +44(0) 1307 452200, e: lotrak@donlow.co.uk w: **www.donlow.co.uk** 

lssue 6 May 2025

C F